

DATA SHEET

TEST ITEM	Test Standard	Unit	TEST RESULTS
Hardness degrees	-	SHORE A	55 (+/-5)
Specific gravity	-	g/cm ³	1,25
Heat resistant	-	°C	-60 / +220
Tensile strenght at break	-	Mpa	7
Tear strength	-	KN/M	20
Elongation at break change	-	%	350
Permanent deformation	-	%	7

KOLO KFT. H-1149 BUDAPEST NAGY LAJOS KIRÁLY ÚTJA 103.
TELEFON: +36 1 221 4756 FAX:36 1 220 0611 MOBIL: +36 30 7090 350
www.kolofol.hu kolofol@kolofol.hu

2014. márc. 19.